

Turbine Bearings Technical Data Sheet

Synthetic esters have a long history of use in aviation jet engine lubricants due to their combination of oxidative stability, low volatility and high viscosity index. Aviation turbine engine bearings demand fluidity at extreme low temperatures and lubrication film strength under high shear and high temperature conditions. Esters have been proven to deliver long life, low deposit formation and reliable lubrication under the most extreme operating conditions.

Synthetic Ester	Chemistry	Viscosity @ 40°C (cSt)	Viscosity @ 100°C (cSt)	Viscosity Index	Flash Pt. (°C)	Pour Pt. (°C)
LUBRICIT DOS	Diester	12	3.2	150	235	-60
LUBRICIT DIDA	Diester	14	3.6	145	230	-60
LEXOLUBE 3Q-310	Polyol	18	4.0	120	250	-65
LUBRICIT TMP C810	Polyol	20	4.4	140	260	-40
LUBRICIT DIDS	Diester	21	4.7	155	240	-50
LUBRICIT TMP C9	Polyol	21	4.6	140	275	-50
LEXOLUBE POE-22	Polyol	22	4.7	140	270	-40
LUBRICIT PE 510/1	Polyol	22	4.7	135	285	-45
LUBRICIT DTDA	Diester	23	4.9	145	245	-55
LUBRICIT 9547	Polyol	25	5.0	135	265	-55
LUBRICIT DTDA/1	Diester	27	5.4	135	250	-60
LEXOLUBE POE-32	Polyol	32	6.0	135	270	-40

Features

- Thermal/oxidative stability
- Low volatility
- No deposit formation
- High viscosity index
- Low temperature fluidity
- High flash point/fire resistance
- Long service life

Applications

- Type I diester lubricants for small private aircraft engines (3 cSt)
- Type II polyol ester lubricants for military and commercial jet engines (3 & 4 cSt)
- Type III polyol ester lubricants for commercial jet engines (5 cSt)
- MIL-PRF-7808L, MIL-PRF-23699G
- SAE-AS5780 for commercial aviation engines

Please inquire about additional tailor-made products that can be made to fit your exact performance requirements.

LEXOLUBE® and LUBRICIT are trade names of Zschimmer & Schwarz Inc.. Zschimmer & Schwarz Inc. and its marketing subsidiaries, affiliates, partners and suppliers, disclaim responsibility for results of use of the Materials or of any product, method, or apparatus mentioned herein. Nothing stated herein is to be considered a recommendation or inducement of any use, manufacture or sale that may infringe any patents or any other proprietary rights now or hereafter in existence. The Materials are intended to act as a guide for use at your discretion and risk. We assume no liability in connection with the use, or the utilization of the Materials or the methods or products described therein. Information pertaining to availability, pricing and technical assistance for these products can be obtained from the marketing department, through the nearest sales representative or authorized distributor. Copyright © 2020 Zschimmer & Schwarz Inc. | All Rights Reserved